



SMITH-EMERY LABORATORIES
An Independent Commercial Testing Laboratory, Established 1904

781 E. Washington Boulevard Los Angeles, California 90021 ♦ (213) 749-3411 ♦ Fax (213) 741-8626

Project/Job No : 35562-1
Laboratory No.: T-07-060

April 24, 2007

Client : **GREG FILLO**
BEDROSIAN'S TILE & MARBLE
1515 E WINSTON ROAD
ANAHEIM, CA 92805

Subject: **TCR EDD33A - 13" x 13" x 3/8" thick Field Tile Eddie Almond Ceramic Tiles, Made in China**
Specification: **ASTM C 1028-96**
Source: Submitted to Smith-Emery Laboratories by Client on April 9, 2007.

STATIC COEFFICIENT OF FRICTION (ASTM C 1028-96)

A block of wood with a 3" x 3" x 1/8" section of standard neolite sole liner attached. was placed on the surface to be tested, on top of this assembly. a 50 pound (22kg) weight was placed Using dynamometer, the force in pounds required to cause the test assembly to slip parallel to the test surface was measured Four measurements were taken on each of three test surfaces. each measurement perpendicular to the previous one The twelve measurements were averaged to obtain the coefficient of friction for each test condition

A. As Received:

Test Condition	Tile No.	N	E	S	W	Average	Individual	S.C.O.F
							Coefficient of Friction (fc)	After Noelite Correction Factor
Dry Neolite	1	43	44	42	43	42.75	(0.83)	0.65
	2	43	42	42	43			
	3	42	44	43	42			
Wet Neolite	1	36	35	36	36	35.83	(0.70)	0.65
	2	36	36	35	36			
	3	36	35	36	37			


B After Cleaning with Hillyards Renovator. (ASTM C 1028 Standard Cleaner)

Dry Neolite	1	41	43	42	42	42.33	(0.83)	0.65
	2	42	43	42	43			
	3	43	42	42	43			
Wet Neolite	1	35	36	35	35	35.67	(0.70)	0.65
	2	36	36	35	36			
	3	36	36	36	36			

Specification: Department of Justice ADA Title III Regulation 28 CFR Part 36, Section A4.5.1; Recommends minimum of 0.60 SCOF for horizontal surfaces and 0.80 SCOF on ramps

Respectfully Submitted,
SMITH - EMERY LABORATORIES

[Signature]
P. John Latiolait
Registered Civil Engineer No. C60312
Registration Expires: 06-30-08
rlm



- Materials Tested Comply With Specifications.
 - Horizontal; Ramps or Incline
- Materials Tested Did Not Comply With Specifications.
- No Established Criteria for Acceptable Limits.
- For Information Only.

CC: BEDROSIAN'S TILE & MARBLE; SMITH-EMERY LABORATORIES