



SMITH-EMERY LABORATORIES

An Independent Commercial Testing Laboratory, Established 1904

781 E. Washington Boulevard Los Angeles, California 90021 ♦ (213) 749-3411 ♦ Fax (213) 741-8626

Proj /Job No : 37139-1
Lab No : T-07-195

November 16, 2007

CLIENT: GREG FILLO
BEDROSIANS
1515 E. WINSTON ROAD
ANAHEIM, CA 92805-6445

Subject: **TCR JOC 50B 19-3/4" x 19-3/4" Field Tile "Jocelyn Beige" Ceramic Tiles (Made in China)**
Specification: CTI Stain Test (CTI-T-72)
Source : Submitted to Smith-Emery Laboratories by Client October 10, 2007.
Date Tested: October 16, 2007

Report of Tests

CERAMIC TILE INSTITUTE STAIN TEST (CTI-T-72)


Procedure

The following stain materials (common household products) were applied to the surface of the tile, with one area covered and a second area uncovered. The stain materials was in contact with the tile surface for 24 hours, then cleaned using Ajax Industrial Cleanser, 3M nylon scrubber and water. Test results are as follows:


Staining Materials	Exposed Time (Hours)	OBSERVATIONS	
		Uncovered	Covered
Coca Cola	24	No Stain	No Stain
Lemon Juice	24	No Stain	No Stain
Mustard	24	No Stain	No Stain
Bacon Grease	24	No Stain	No Stain
Catsup	24	No Stain	No Stain
Wesson Oil	24	No Stain	No Stain

Respectfully Submitted.

SMITH - EMERY LABORATORIES


P. John Laticlait
Registered Civil Engineer No. C60312
Registration Expires: 06-30-08

JLM



- Materials Tested Comply With Specifications.
- Materials Tested Did Not Comply With Specifications.
- No Established Criteria For Acceptable Limits.

CC: BEDROSIANS; SMITH-EMERY LABORATORIES