



# SMITH-EMERY LABORATORIES

An Independent Commercial Testing Laboratory. Established 1904

781 E. Washington Boulevard Los Angeles, California 90021 ♦ (213) 749-3411 ♦ Fax (213) 741-8626

Project/Job No.: 35562-1  
Laboratory No.: T-06-142

July 13, 2006

Client : GREG FILLO  
BEDROSIANS  
1123 E. WARNER AVENUE  
TUSTIN, CA 92780

Subject: 13 inch x 13 inch TCR LIM 33S "Field Time Silver Bedrosian Porcelain Tile (Made in China)  
Specification: ASTM C 1028-96  
Source: Submitted to Smith-Emery Laboratories by Client.

### STATIC COEFFICIENT OF FRICTION (ASTM C 1028-96)

A block of wood with a 3" x 3" x 1/8" section of standard neolite sole liner attached, was placed on the surface to be tested; on top of this assembly, a 50 pound (22kg) weight was placed Using dynamometer. the force in pounds required to cause the test assembly to slip parallel to the test surface was measured. Four measurements were taken on each of three test surfaces, each measurement perpendicular to the previous one. The twelve measurements were averaged to obtain the coefficient of friction for each test condition.

#### A. As Received:

Test Condition	Tile No.	N	E	S	W	Average	Individual	S.C.O.F
							Coefficient of Friction (fc)	After Neolite Correction Factor
Dry Neolite	1	46	47	47	46	46.33	(0.90)	0.72
	2	45	46	47	46			
	3	46	47	47	46			
Wet Neolite	1	31	29	30	30	30.25	(0.59)	0.53
	2	31	30	30	31			
	3	30	30	31	30			

#### B. After Cleaning with Hillyards Renovator. (ASTM C 1028 Standard Cleaner)

Dry Neolite	1	46	46	47	47	46.42	(0.91)	0.73
	2	47	47	46	46			
	3	46	46	47	46			
Wet Neolite	1	30	28	29	29	29.33	(0.57)	0.51
	2	30	29	30	30			
	3	30	29	30	28			

Specification: Department of Justice ADA Title III Regulation 28 CFR Part 36, Section A4.5.1; Recommends minimum of 0.60 SCOF for horizontal surfaces and 0.80 SCOF on ramps.

Respectfully Submitted,  
SMITH-EMERY LABORATORIES

V. Andrew Tan  
Registered Civil Engineer No. C64265  
Registration Expires: 06-30-07



- Materials Tested Comply With Specifications.
  - Horizontal;  Ramps or Incline
- Materials Tested Did Not Comply With Specifications.
- No Established Criteria for Acceptable Limits.
- For Information Only.

BEDROSIANS;SMITH-EMERY LABORATORIES

F:\PHYLAB\C\_EXCELNTILE LAB 2006\35562 BEDROSIANSJOB NT-06-142

Page 1 of 1

ALL REPORTS ARE SUBMITTED AS THE CONFIDENTIAL PROPERTY OF CLIENTS. AUTHORIZATION FOR PUBLICATION OF OUR REPORT, CONCLUSIONS, OR EXTRACTS FROM OR REGARDING THEM IS RESERVED PENDING OUR WRITTEN APPROVAL AS A MUTUAL PROTECTION TO CLIENTS, THE PUBLIC AND OURSELVES



# SMITH-EMERY LABORATORIES

An Independent Commercial Testing Laboratory. Established 1904

781 E. Washington Boulevard Los Angeles, California 90021 ♦ (213) 749-3411 ♦ Fax (213) 741-8626

Project No: 35562-1  
Lab No: T-06-149

August 22, 2006

CLIENT: GREG FILLO  
BEDROSIANS  
1123 E. WARNER AVENUE  
TUSTIN, CA 92780

SUBJECT: TCR LIM 33S - 13" x 13" x 5/16" Thick Field Tile - Silver Porcelain (Made in China)  
Specification : MOHS Hardness Test (MOHS Scale)  
Source : Submitted to Smith-Emery Laboratories by Client on July 17, 2006.  
Date Tested: 8/1/06

## REPORT OF TEST

### SCRATCH HARDNESS OF SURFACE (MOHS SCALE)

A sharp angular mineral starting with hardness one (1) on the MOHS Scale is drawn while applying a uniform pressure across the surface of the tile. The highest hardness number with which no scratches visible to the naked eye occur shall be taken as the result of the test


AREA	SAMPLE NUMBER	MOHS SCALE	MINERAL EQUIVALENT
	1	7.0	Quartz
	2	7.0	Quartz
Top Surface Only	3	7.0	Quartz
	4	7.0	Quartz
	5	7.0	Quartz

### MOHS Table

Mohs #	Mineral	Mohs #	Mineral
1.0	Talc	6.0	Microcline
2.0	Selenite	7.0	Quartz
3.0	Calcite	8.0	Topaz
4.0	Fluorite	9.0	Corundum
5.0	Apatite	10.0	Diamond

Respectfully Submitted,  
SMITH - EMERY LABORATORIES

V. Andrew Tan  
Registered Civil Engineer No.: C64265  
Registration Expires: 06-30-07



- Materials Tested Comply With Specifications.
- Materials Tested Did Not Comply With Specifications.
- No Established Criteria For Acceptable Limits.

mc

Cc: BEDROSIANS; SMITH-EMERY LABORATORIES