



SMITH-EMERY LABORATORIES

An Independent Commercial Testing Laboratory, Established 1904

781 E. Washington Boulevard Los Angeles, California 90021 ♦ (213) 749-3411 ♦ Fax (213) 741-8626

Proj No.: 37139-1
Lab No.: T-07-144

August 20, 2007

Client : GREG FILLO
BEDROSIANS
1515 E WINSTON ROAD
ANAHEIM, CA 92805-6445

Subject: (TCR MGT 0566) 6" x 6" Field Tile 05, "Madelyne Taupe" Glass Tiles
Specification : ASTM C-650 (Qualitative Observation Only)
Source : Submitted to Laboratory by Client.

Report of Tests

CHEMICAL RESISTANCE OF CERAMIC TILE (ASTM C 650)

Exposure time : 24 hours

Room temperature : 75.5 °F

<u>Tile Number</u>	<u>Acid 10% HCL</u>	<u>Alkali 10% KOH</u>
1.	Unaffected	Unaffected
2.	Unaffected	Unaffected
3.	Unaffected	Unaffected
4.	Unaffected	Unaffected
5.	Unaffected	Unaffected
6.	Unaffected	Unaffected


Requirements : No Requirement

Remarks : Sample Tested Shows no Physical Damage After Test

Respectfully Submitted,

SMITH - EMERY LABORATORIES

P John Latiolait
Registered Civil Engineer No. C60312
Registration Expires: 06-30-08



- The materials tested comply with specifications.
- The materials tested did not comply with specification:
- No established criteria for acceptable limits.

dp

CC: BEDROSIANS; SMITH-EMERY LABORATORIES